

Solid Acrylic Resin PChem[®] BM46

1. BM46 is a thermoplastic solid acrylic resin with excellent weatherability, higher hardness, and flexibility.
2. BM46 is easily soluble in many organic solvents such as ketones, esters, long-chain fatty alcohol and aromatic hydrocarbons, and also has good compatibility with other film forming resins such as cellulose, epoxy resin, vinyl resin and other acrylic resin.
3. BM46 can enhance the phase's stability, dryness and pigment dispersion for PVDF resin. With its outstanding performance of adhesion on metal substrates (especially at post-baking process), BM46 is widely used in baking-type fluorocarbon coatings (PVDF coatings).

	Item	Value	Unit	Test method
Specifications	Appearance	Pellets		
	Glass transition temperature (Tg)	82	°C	ASTM D-3418
	Molecular weight (Mw)	100,000	g/mol	ASTM D-3593
	Inherent viscosity (IV)	0.40		ASTM D-2857
	Acid value	≤ 1.0	mgKOH/g	ISO-3682
	Moisture content	≤ 0.5	%	ISO-3251

◆ Packaging and storage

1. Packed in composite paper bag with inner plastic bag, 25kg net.
2. Store in cool, dry and ventilated place where the fire and organic solvents are prohibited.
3. Shelf life: 3 years, capable of further use after passing QC inspection.
4. Transport as non-dangerous material.

Notes: The information contained on above data sheet is, to the best of our current knowledge, true and accurate. However, since the conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liabilities in connection with the use of information contained herein or otherwise. All risks of such nature are assumed by the user.